

AMERICOLENE® LDAP5321



Liner LDPE Resin with Slip and Antiblock

Americolene[®] LDAP5321 is a low density polyethylene offering good balance of optical and mechanical properties. Americolene t[®] LDAP5321 is formulated with slip and antiblock for use in film applications offering excellent extrusion processing and film optical properties.

Suggested Applications:

Blend Partner Light Duty Shrink Film Mail Bags
Cast Film Freezer Film Produce Bags
Food Packaging Lamination Film Shoppers

Foams Compounding Textile Packaging

Liners Form Fill and Seal Packaging

Nominal Physical Properties:

| | TEST | | |
|--|--------|----------|--------------|
| PROPERTY | METHOD | UNIT | VALUE |
| Density | D1505 | g/cc | 0.923 |
| Melt Index, Condition E, 190C°/2.16 kg | D1238 | g/10 min | 2.0 |
| Dart Impact | D1709 | g | 80 |
| Elmendorf Tear Strength | D1922 | g | 150/120* |
| Tensile Strength at Yield | D882 | psi | 1600/1600* |
| Tensile Strength at Break | D882 | psi | 3600/3200* |
| Elongation at Break | D882 | % | 330/550* |
| Secant Modulus @ 1% | D882 | psi | 30000/33000* |
| Gloss (45°) | D2457 | | 63 |
| Haze | D1003 | % | 6.1 |

^{*} MD / TD

Note: Film properties based on $1.5 \, \text{mil}$ (38.1 micron) thick film produced on a $2.5 \, \text{inch}$ (63.5 mm) blown film line with a $2.5:1 \, \text{blowup}$ ratio, a melt temperature of $340\text{-}360^{\circ}\text{F}$ (171-182°C), a 30 mil (0.76 mm) die gap at a rate of 8 lbs/hr/in die circumference (1.43kg/hr/cm). Actual film properties may vary based on extrusion equipment, operating conditions and additive package. Film properties are not intended to be used as specifications.

Published 12/1/2021

 $Inquiries\ regarding\ this\ data\ sheet\ should\ be\ addressed\ to:\ 11824\ Jollyville\ Rd\ Austin,\ TX\ 78759\cdot Phone\ (800)\ 729\ 5417\cdot Fax:\ (512)\ 992\ 0225$

The information and recommendation in this publication are, to the best of knowledge, reliable. Suggestions concerning uses are only the opinion of AMERICORP INTERNATIONAL LTD, U.S.A. and users should perform their own tests to determine the suitability of this products for their own particular purposes. However, because of the numerous factors affecting the results, AMERICORP INTERNATIONAL LTD, U.S.A. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSES, other than that the material conforms to the applicable current standard specifications statement herein, therefor, should not be construed as representations or warranties. The responsibility of AMERICORP INTERNATIONAL LTD, U.S.A. for claims arising out of breach warranty, negligence, and strict liability or otherwise is limited to the purchase price of the material. Statement concerning the use of the products of AmeriCorp described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed