

AMERICOLENE® AR40039E

AMERICOLENE

Linear Low Density Polyethylene

Product Description

Americolene® AR40039E is a linear medium density polyethylene selected by customers for rotomolding a variety of objects, including drums, agricultural and chemical storage containers, playground equipment and municipal trash containers. AR40039E is UV-stabilized and is also available in 35-mesh powder as Microthene MP643962.

Regulatory Status

For regulatory compliance information, see Americolene® AR40039E Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS).

Status	Commercial: Active
Availability	North America
Application	Containers; Drums; Intermediate Bulk Containers; Jerry Cans; Sports, Leisure & Toys
Market	Rigid Packaging
Processing Method	Rotomolding

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	3.6	g/10 min	3.6	g/10 min	ASTM D1238
Density, (23 °C)	0.9395	g/cm ³	0.9395	g/cm ³	ASTM D1505
Mechanical					
Flexural Modulus					
(1% Secant)	119000	psi	820	MPa	ASTM D790
(2% Secant)	101000	psi	700	MPa	ASTM D790
Tensile Strength at Yield	2900	psi	20.0	MPa	ASTM D638
Environmental Stress Crack Resistance, F50 (100% Igepal®, Cond A)	>1000	hr	>1000	hr	ASTM D1693
Impact					
Low Temperature Impact					
1/8" specimen @ -40 °F	54	ft-lbs	55	J	ARM
1/4" specimen @ -40 °F	160	ft-lbs	215	J	ARM
Thermal					
Deflection Temperature Under Load					
(66 psi, Unannealed)	136	°F	58	°C	ASTM D648
(264 psi, Unannealed)	104	°F	40	°C	ASTM D648

Any inquiries regarding this data sheet should be addressed to: 11824 Jollyville Rd Austin, TX 78759 · Phone (800) 729 5417 · Fax: (512) 992 0225

The information and recommendation in this publication are, to the best of knowledge, reliable. Suggestions concerning uses are only the opinion of AMERICORP INTERNATIONAL LTD, U.S.A. and users should perform their own tests to determine the suitability of this products for their own particular purposes. However, because of the numerous factors affecting the results, AMERICORP INTERNATIONAL LTD, U.S.A. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSES, other than that the material conforms to the applicable current standard specifications statement herein, therefor, should not be construed as representations or warranties. The responsibility of AMERICORP INTERNATIONAL LTD, U.S.A. for claims arising out of breach warranty, negligence, and strict liability or otherwise is limited to the purchase price of the material. Statement concerning the use of the products of AmeriCorp described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed