

AMERICOLENE® L7022-IM

AMERICOLENE

Low Density Polyethylene

Product Description

AMERICOLENE® L7022-IM is selected by customers for use in both extrusion coating and injection molding applications. L7022-IM is a high speed, lightweight coating resin for use with paper, films and other base stocks. This resin can be extruded at line speeds of 1200 ft/min or higher. Products made from materials coated with L7022-IM typically include general-purpose flexible packaging and snack food packaging. L7022-IM yields excellent adhesion and heat sealing characteristics and low neck-in. When L7022-IM is used in injection molding applications, it exhibits an excellent balance of toughness and softness, with excellent dimensional stability. Typical injection molding applications include housewares, toys, containers and novelty items.

Regulatory Status

For regulatory compliance information, see AMERICOLENE® L7022-IM Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS).

Typical applications include:

Availability	North America
Application	Bags & Pouches; Caps & Closures; Colour Concentrates; Food Packaging Film; Lamination Film; Sealants
Market	Flexible Packaging; Rigid Packaging
Processing Method	Extrusion Coating; Injection Molding

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	7.0	g/10 min	7.0	g/10 min	ASTM D1238
Density, (23 °C)	0.918	g/cm ³	0.918	g/cm ³	ASTM D1505
Mechanical					
Flexural Modulus, (1% Secant)	31900	psi	233	MPa	ASTM D790
Tensile Strength at Break	1730	psi	12.1	MPa	ASTM D638
Tensile Strength at Yield	1430	psi	10.1	MPa	ASTM D638
Tensile Elongation at Break	550	%	550	%	ASTM D638
Tensile Elongation at Yield	19	%	19	%	ASTM D638
Hardness					
Shore Hardness, (Shore D)	50		50		ASTM D2240
Thermal					
Vicat Softening Temperature	186	°F	86	°C	ASTM D1525
Processing Parameters					
Melt Temperature	<=625	°F	<=329	°C	

Any inquiries regarding this data sheet should be addressed to: 11824 Jollyville Rd Austin, TX 78759 · Phone (800) 729 5417 · Fax: (512) 992 0225

The information and recommendation in this publication are, to the best of knowledge, reliable. Suggestions concerning uses are only the opinion of AMERICORP INTERNATIONAL LTD, U.S.A. and users should perform their own tests to determine the suitability of this products for their own particular purposes. However, because of the numerous factors affecting the results, AMERICORP INTERNATIONAL LTD, U.S.A. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSES, other than that the material conforms to the applicable current standard specifications statement herein, therefor, should not be construed as representations or warranties. The responsibility of AMERICORP INTERNATIONAL LTD, U.S.A. for claims arising out of breach warranty, negligence, and strict liability or otherwise is limited to the purchase price of the material. Statement concerning the use of the products of AmeriCorp described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed