

# AMERICOLENE® LL118WJ

**AMERICOLENE**

## Low Density Polyethylene

### Product Description

The AMERICOLENE® LL118WJ series of resins is pelletized linear low density polyethylene selected by customers for film extrusion applications that require excellent drawdown and toughness. These resins have excellent puncture resistance, elongation and heat seal strength. Typical applications include heavy duty shipping sacks, trash can liners, commercial and industrial packaging, as well as food and consumer packaging. LL118WJ is available without additives or fully formulated with slip and antiblock additives.

### Regulatory Status

For regulatory compliance information, see AMERICOLENE® LL118WJ Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS).

<b>Status</b>	Commercial: Active
<b>Availability</b>	North America
<b>Application</b>	Agriculture Film; Bags & Pouches; Can Liners; Film Wrap; Food Packaging Film; Heavy Duty Packaging; Lamination Film; Liner Film; Retail Carryout Bags; Shrink Film
<b>Market</b>	Flexible Packaging
<b>Processing Method</b>	Blown Film

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
<b>Physical</b>					
Melt Flow Rate, (190 °C/2.16 kg)	1.0	g/10 min	1.0	g/10 min	ASTM D1238
Base Resin Density, (23 °C)	0.918	g/cm <sup>3</sup>	0.918	g/cm <sup>3</sup>	ASTM D1505
Product Density, (23 °C)	0.923	g/cm <sup>3</sup>	0.923	g/cm <sup>3</sup>	ASTM D1505
<b>Film</b>					
Dart Drop Impact Strength, F50	100	g	100	g	ASTM D1709
Tensile Strength at Break					
MD	6600	psi	45.5	MPa	ASTM D882
TD	4700	psi	32.4	MPa	ASTM D882
Tensile Elongation at Break					
MD	580	%	580	%	ASTM D882
TD	725	%	725	%	ASTM D882
1% Secant Modulus					
MD	27000	psi	186	MPa	ASTM D882
TD	28000	psi	193	MPa	ASTM D882
Elmendorf Tear Strength					
MD	125	g	125	g	ASTM D1922
TD	330	g	330	g	ASTM D1922
<b>Thermal</b>					
Vicat Softening Point	225	°F	107	°C	ASTM D1525
<b>Additive</b>					
Slip	1350	ppm	1350	ppm	LYB Method
Antiblock	7000	ppm	7000	ppm	LYB Method
Polymer Processing Aid	None		None		LYB Method

**Any inquiries regarding this data sheet should be addressed to: 11824 Jollyville Rd Austin, TX 78759 · Phone (800) 729 5417 · Fax: (512) 992 0225**

The information and recommendation in this publication are, to the best of knowledge, reliable. Suggestions concerning uses are only the opinion of AMERICORP INTERNATIONAL LTD, U.S.A. and users should perform their own tests to determine the suitability of this products for their own particular purposes. However, because of the numerous factors affecting the results, AMERICORP INTERNATIONAL LTD, U.S.A. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSES, other than that the material conforms to the applicable current standard specifications statement herein, therefor, should not be construed as representations or warranties. The responsibility of AMERICORP INTERNATIONAL LTD, U.S.A. for claims arising out of breach warranty, negligence, and strict liability or otherwise is limited to the purchase price of the material. Statement concerning the use of the products of AmeriCorp described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed