

AMERICOLENE® PS 325-HI

AMERICOLONO

Polystyrene

Description

Polystyrene 825: The high impact polystyrene for injection molding. This easy processing grade allows fast cycle times with minimal post stress resulting in outstanding impact retention. Advanced rubber particle size control makes this polymer the choice for all high gloss applications.

Application:

- · Appliance housings
- · Housewares and toys
- Structural foam
- Refrigeration applications

General Information:

- This material complies with FDA requirements as described in 21 CFR §177.1640.
- This material holds Underwriters Laboratory recognition 94HB; see UL File E55470 at www.UL.com.
- USP Class VI
- Material Safety Data Sheets are available to help customers satisfy their safety needs.

Characteristics

	Method	Unit	Typical Value
Rheological Properties			
Melt Flow (200°C-5kg)	D-1238	g/10mn	8.0
Mechanical Properties			
Falling Dart	D-3029	in-lb	110
Izod - notched	D-256	ft-lbs/in	2.0
Tensile Strength	D-638	psi	3,600
Tensile Modulus	D-638	psi (10⁵)	3.3
Elongation	D-638	%	45
Flexural Strength	D-790	psi	6,500
Flexural Modulus	D-790	psi (10⁵)	3.4
Thermal Properties			
Heat Distortion - Annealed	D-648	°F	193
Vicat Softening	D-1525	°F	205
Other Physical Properties			
Gloss	D-523	60°	90
Density		g/cm³	1.04
Linear Shrinkage	D-955	in/in	.004007
Moisture		%	<0.1

Any inquiries regarding this data sheet should be addressed to: 11824 Jollyville Rd Austin, TX 78759 · Phone (800) 729 5417 · Fax: (512) 992 0225

The information and recommendation in this publication are, to the best of knowledge, reliable. Suggestions concerning uses are only the opinion of AMERICORP INTERNATIONAL LTD, U.S.A. and users should perform their own tests to determine the suitability of this products for their own particular purposes. However, because of the numerous factors affecting the results, AMERICORP INTERNATIONAL LTD, U.S.A. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSES, other than that the material conforms to the applicable current standard specifications statement herein, therefor, should not be construed as representations or warranties. The responsibility of AMERICORP INTERNATIONAL LTD, U.S.A. for claims arising out of breach warranty, negligence, and strict liability or otherwise is limited to the purchase price of the material. Statement concerning the use of the products of AmeriCorp described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed